



Steel Re-Nu® Stainless Steel Coating, 13 Wt Oz

No. 18211 | Item# 1005234 | Case# 1005233

Product Description

A coating containing 316L Stainless Steel pigment to provide corrosion resistance and protection against sunlight, oil, and water. Authorized for use in food processing plants.

Color

Gray

Applications

On threads, exposed edges, fasteners, conduit, strapping, welds, fencing, railings, grates, electrical poles, breaker panel housings, rain spouts, signs, doors, trailers, waste containers, catwalks, and guard rails.

Unit Package Description

16 Ounce Aerosol

Brand

CRC

Generic Description 1

316L Stainless Steel Coating

Net Fill

13 Wt Oz

UPC Code

078254182117

Unit Dimensions

7.75H x 2.63W x 2.63D in

Units Per Case

6

Case Dimensions

8.25H x 5.75W x 8.25D in

Cases Per Pallet

150

Case Weight

7 lbs

I 2 of 5 Code

30078254182118

Appearance

Gray Viscous Liquid

Flash point (F)

-2°F

Flash point (C)

-19°C

Flammability Class - CPSC

Extremely Flammable

Spec Gravity Concentrate

0.77 to 0.85

Plastic Safe

Yes

Dry Time - Fully Dry

20 Minutes

Dry Time - Tack Free

20 Minutes

Recoat

Anytime

Coverage

28 to 32 Sq Ft at 3 Mil Dry

Last revised: 7/30/2019

Page 1 of 2



Chemical Solutions to Keep You Moving™
f t y i n • 800-272-8963 • crcindustries.com

CRC Industries, Inc. is a global leader in the production of specialty chemicals for maintenance, repair and operational professionals and do-it-yourselfers serving the automotive, industrial, electrical, marine, heavy truck, hardware and aviation markets. CRC trademarked brands include: CRC®, K&W®, Sta-Lube®, SmartWasher®, Marykate®, Weld-Aid®, Ambersil®, KF®, Kontakt Chemie®, Ados®, Action Can®, and Kitten®.

©2019 CRC Industries, Inc.



Working Temp (F)	130°F (Continuous) / 150°F (Intermittent)
Working Temp (C)	54.4°C (Continuous) / 65.6°C (Intermittent)
Propellant	Hydrocarbon
NSF Category Code	R2
NSF Number	150841
Aerosol Flammability Level	III
DOT Proper Shipping Name	Aerosols, Flammable, Limited Quantity
VOC % (Consumer Product def)	59.3
VOC g/L (Consumer Product def)	619
VOC lbs/gal (Consumer Prod def)	5.2
VOC Category	Aerosol Coating: Metallic
MIR Limit (EPA)	1.9
MIR Limit (CA)	1.25
MIR Value	1.24
Removal (How To)	Remove with aromatic solvents, Xylene. Toluene can be used, but is not recommended.

